

Table 1 - Summary of Results

Date	Atlantic Sample #	Layer	Diagram location number	Building area	Location (refer to diagrams)	Suspect material	Friability	Condition of Friable ACM	H.A.	Estimated Quantity of Homogeneous ACM	% asbestos
9/17/16	I1716-301	n/a	1	2FL	Kitchen	Green vinyl flooring	Non-friable	n/a	A	180 s.f.	20.6%
9/17/16	I1716-302	n/a	2	2FL	Kitchen	Green vinyl flooring	Non-friable	n/a	A		PS
9/17/16	I1716-303	n/a	3	2FL	Bath	White vinyl flooring	Non-friable	n/a	B	n/a	NAD
9/17/16	I1716-304	n/a	4	2FL	Bath	White vinyl flooring	Non-friable	n/a	B	n/a	NAD
9/17/16	I1716-305	n/a	5	2FL	Front	Textured paint	Friable	n/a	C	n/a	NAD
9/17/16	I1716-306	n/a	6	2FL	Front	Textured paint	Friable	n/a	C	n/a	NAD
9/17/16	I1716-307	n/a	7	2FL	Attic stair	Plaster	Friable	n/a	D	n/a	NAD
9/17/16	I1716-308	n/a	8	2FL	Attic stair	Plaster	Friable	n/a	D	n/a	NAD
9/17/16	I1716-309	n/a	9	1FL	LR	Plaster	Friable	n/a	D	n/a	NAD
9/17/16	I1716-310	n/a	10	1FL	LR	Plaster	Friable	n/a	D	n/a	NAD
9/17/16	I1716-311	n/a	11	1FL	LR	Plaster	Friable	n/a	D	n/a	NAD
9/17/16	I1716-312	n/a	12	1FL	Kitchen	Green vinyl flooring	Non-friable	n/a	E	330 s.f.	14.6%
9/17/16	I1716-313	n/a	13	1FL	Kitchen	Green vinyl flooring	Non-friable	n/a	E		PS
9/17/16	I1716-314	n/a	14	1FL	Rear hall	Wallpaper	Friable	n/a	F	n/a	NAD
9/17/16	I1716-315	n/a	15	1FL	Rear hall	Wallpaper	Friable	n/a	F	n/a	NAD
9/17/16	I1716-316	n/a	16	1FL	LR	1.5x1.5 ceiling tile	Friable	n/a	G	n/a	NAD
9/17/16	I1716-317	n/a	17	1FL	LR	1.5x1.5 ceiling tile	Friable	n/a	G	n/a	NAD
9/17/16	I1716-318	n/a	18	1FL	LR	2x4 ceiling tile (new)	Friable	n/a	H	n/a	NAD
9/17/16	I1716-319	n/a	19	1FL	LR	2x4 ceiling tile (new)	Friable	n/a	H	n/a	NAD
9/17/16	I1716-320	n/a	20	1FL	LR	2x4 ceiling tile (old)	Friable	n/a	I	n/a	NAD
9/17/16	I1716-321	n/a	21	1FL	LR	2x4 ceiling tile (old)	Friable	n/a	I	n/a	NAD
9/17/16	I1716-322	n/a	22	1FL	LR	Drywall	Friable	Good	J	5,000 s.f.	Presumed
9/17/16	I1716-323	n/a	23	1FL	LR	Joint compound	Friable	Good	J		3.5%
9/17/16	I1716-324	n/a	24	1FL	LR	Drywall	Friable	Good	J		PS
9/17/16	I1716-325	n/a	25	1FL	LR	Joint compound	Friable	Good	J		PS
9/17/16	I1716-326	n/a	26	Basement	Wall	Parging	Friable	n/a	K	n/a	NAD
9/17/16	I1716-327	n/a	27	Basement	Wall	Parging	Friable	n/a	K	n/a	NAD
9/17/16	I1716-328	n/a	28	Basement	Chimney	Flue cement	Friable	n/a	L	n/a	NAD

Table 1 Notes:

Orange highlighting indicates samples with greater than 1% asbestos - POSITIVE or presumed

NAD = No asbestos

PS = Positive Stop: the sample or layered system is presumed to contain asbestos

H.A. = Homogeneous Area